

1015

SEMI-HARD TRIFLEX™

March 2015

Polycorp 1015 is a black 50D surface durometer “Triflex™” consisting of a semi-hard face stock with a hard natural rubber center layer and a soft natural rubber tie gum. The lining has excellent chemical and permeation resistance properties. Operating temperature range is from 50°F (10°C) to 185°F (85°C)

APPLICATION NOTES:

- **Skive** – use closed skive construction.
- **Repair** – Same or 1038 semi-hard chemical cure. Refer to section 11 of application manual
- **Cured Durometer** – Shore D durometer on top surface 50 ± 10.
- **Spark Test** – Refer to section 13 of the Application Manual

ADHESIVE NOTES:

See Section 6 of the Polycorp Rubber Lining Application Manual for specific cementing / adhesion notes. For proper adhesion, temperatures must be over 60°F (15°C) and must not exceed 120°F (49°C). Use adhesives in well-ventilated area and always consult the material safety data sheet for specific precautions.

CURING:

Cure time adjustments may be required to compensate for specific conditions. See Section 10 of the Application Manual for detailed instructions.

Autoclave Method – 3/16” and 1/4” thickness: 1 hour rise to 260°F/127°C (20 psi) hold @ 260°F for 2½ hours

Internal Steam Method - 3/16” and 1/4” thickness:
 7 hours @ 260°F/127°C (20 psi).
 12 hours @ 250°F/121°C (15 psi).
 22 hours @ 240°F/116°C (10psi).

Atmospheric Steam Method – 1/4” thickness:
 Minimum 40 hours @ 212°F/100°C
 Lower durometer will result with this type of cure.

Coat	Polycorp Adhesive	Approved Equivalent
1 st Coat on Metal	C-90 Primer	Chemlok 289
2 nd Coat on Metal	C-91 Intermediate	Chemlok 290
3 rd Coat on Metal	C-202S Tack	Chemlok 286
4 th Coat on lining	C-202S Tack	Chemlok 286

STORAGE:

Store in a cool and dry area.

Shelf Life	
Stored below 50°F (10°C)	180 days
Stored between 51 and 70°F	90 days
Stored between 71 and 90°F	45 days
Do not store above 90°F (32°C)	

Depending on storage conditions it may be possible to use rubber linings beyond the recommended shelf life however additional testing must be completed. Please contact Polycorp for recommended test procedures. A sample of the rubber lining can also be sent back to Polycorp for verification.

Storage, handling and application methods must conform to the Polycorp Rubber Lining Application Manual.

TYPICAL PROPERTIES:

Property	Value	ASTM Test Method
Hardness (Face) (points)	50 D ± 10	D2240
Tensile Strength (min, psi)	N/A	D412
Elongation at Break (min, %)	N/A	D412
Specific Gravity	1.22	D297
Adhesion to Metal (min, lbf/in)	25	D429
Operating Temperature Range for Optimum Service Life	50°F (10°C) to 185°F (85°C)	N/A

All physical property values developed and measured using a press-cured sample sheet prepared in accordance with ASTM D3182.

PRECAUTIONS:

- This is a hard rubber compound. Over-cure will cause brittleness.
- Do not use in transport equipment or tanks to be installed outside.
- This lining may not be suitable for equipment that may be exposed to extremely low temperatures. If temperatures will be below 32 °F/0 °C, contact Polycorp with all the service conditions for a specific recommendation.
- Cool down to 120 °F/49 °C before releasing pressure during pressure cure.
- Do not ship lined tank below 20 °F