

1058

CHEMICAL CURE CHLOROBUTYL LINING

May 2014

Polycorp 1058 is a white 40A durometer chemical cure chlorobutyl. It is a general purpose repair stock for white chlorobutyl lining. It provides general chemical resistance in applications up to 200°F/93°C. It is FDA compliant as per 21CFR177.2600. For FDA application use cure activator C-600 otherwise use cure activator C-700. Operating temperature range is from -4°F (-20°C) to 200°F (93°C).

APPLICATION NOTES:

- **Skive** – use closed skive construction
- **Repair** – Same. Refer to section 11 of application manual
- **Cured Durometer** – Shore A durometer of top surface: 40 ± 10.
- A heated table to warm the rubber to 110–120°F (43°C) is recommended
- **Spark Test** – Refer to section 13 of the Application Manual

ADHESIVE NOTES:

See Section 6 of the Polycorp Rubber Lining Application Manual for specific cementing / adhesion notes. For proper adhesion, temperatures must be over 60°F (15°C) and must not exceed 120°F (49°C). Use adhesives in well-ventilated area and always consult the material safety data sheet for specific precautions.

CURING:

Cure time adjustments may be required to compensate for specific conditions. See Section 10 of the Application Manual for detailed instructions.

Ambient: The chemical cure lining will vulcanize in about three (3) weeks at 75°F/24°C. If service temperature is about 150°F/66°C, the lining can be immediately put into service.

Atmospheric Steam Assist: Introduce exhaust steam sufficient to insure contact with all surfaces. Approximately 6-8 hours in exhaust steam will be required to cure lining. More time may be necessary in a large tank, or if heat losses are large.

Coat	Polycorp Adhesive	Approved Equivalent
1 st Coat on Metal	C-90 Primer	Chemlok 289
2 nd Coat on Metal	C-91 Intermediate	Chemlok 290
3 rd Coat on Metal	C-204S Tack	C-204S Tack
4 th Coat on lining	C-204S Tack	C-204S Tack

STORAGE:

Store in a cool and dry area.

Shelf Life	
Stored below 50°F (10°C)	180 days
Stored between 51 and 70°F	90 days
Stored between 71 and 90°F	45 days
Do not store above 90°F (32°C)	

Depending on storage conditions it may be possible to use rubber linings beyond the recommended shelf life however additional testing must be completed. Please contact Polycorp for recommended test procedures. A sample of the rubber lining can also be sent back to Polycorp for verification.

Storage, handling and application methods must conform to the Polycorp Rubber Lining Application Manual.

TYPICAL PROPERTIES:

Property	Value	ASTM Test Method
Hardness (Face) (points)	40 A ± 5	D2240
Tensile Strength (min, psi)	1000	D412
Elongation at Break (min, %)	400	D412
Specific Gravity	1.40	D297
Adhesion to Metal (min, lbf/in)	25	D429
Operating Temperature Range for Optimum Service Life	-4°F (-20°C) to 200°F (93°C)	N/A

All physical property values developed and measured using a press-cured sample sheet prepared in accordance with ASTM D3182.

SPECIAL TREATMENT AFTER APPLICATION:

- After application, brush the rubber surface with three (3) separate coats of C-600 activator for FDA application or C700 for Non-FDA application.
- Allow to dry 30 minutes between each coat.