

2006

CHLOROBUTYL WITHOUT TIE GUM

January 2020

Polycorp 2006 is a 50A durometer “Pure” black chlorobutyl rubber lining. It provides excellent chemical resistance at elevated temperature. Specially developed to handle strong sodium hypochlorite solution up to 15% available chlorine. It is also suitable for 70% hydrofluoric acid service.

APPLICATION NOTES:

- **Skive** – use lap or skive-butt joint covered with 2007 cap strip (4” wide x1/8” thick)
- **Repair** – Same. Refer to section 11 of application manual.
- **Cured Durometer** – Shore A Durometer of top surface: 50 ± 5.
- A heated table to warm the rubber to 110–120°F (43°C) is recommended
- **Spark Test** – Refer to section 13 of the Application Manual

ADHESIVE NOTES:

See Section 6 of the Polycorp Rubber Lining Application Manual for specific cementing / adhesion notes. For proper adhesion, temperatures must be over 60°F (15°C) and must not exceed 120°F (49°C). Use adhesives in well ventilated area and always consult the material safety data sheet for specific precautions.

CURING:

Cure time adjustments may be required to compensate for specific conditions. See Section 10 of the Application Manual for detailed instructions.

Autoclave Method – Up to 1/4” thickness:

1 1/2 hours @ 260°F/127°C (20 psi) or 1 hour at 292°F /144°C (45 psi)

Internal Steam Method – Up to 1/4” thickness:

7 hours @ 260°F/127°C (20 psi); or
12 hours @ 240°F/116°C (10 psi).

Atmospheric Steam Method – Up to 1/4”

thickness: Minimum 24 hours @ 212°F/100°C.

Coat	Polycorp Adhesive	Approved Equivalent
1 st Coat on Metal	C-100 Primer	Chemlok 205
2 nd Coat on Metal	Chemlok 6411	Chemlok 6411
3 rd Coat on Metal	0147HE2S CB Tack	N/A

4 th Coat on lining	0147HE2S CB TACK	N/A
--------------------------------	---------------------	-----

STORAGE:

Store in a cool, dry area.

Shelf Life	
Stored below 50°F (10°C)	180 days
Stored between 51 and 70°F	60 days
Stored between 71 and 90°F	45 days
Do not store above 90°F (32°C)	

Depending on storage conditions it may be possible to use rubber linings beyond the recommended shelf life however additional testing must be completed. Please contact Polycorp for recommended test procedures. A sample of the rubber lining can also be sent back to Polycorp for verification.

Storage, handling and application methods must conform to the Polycorp Rubber Lining Application Manual.

TYPICAL PROPERTIES:

Property	Value	ASTM Test Method
Hardness (Face)	50 A ± 5	D2240
Tensile Strength (min, psi)	1200	D412
Elongation at Break (min, %)	400	D412
Specific Gravity	1.21	D297
Adhesion to Metal (min, lbs)	25	D429

All physical property values developed and measured using a press-cured sample sheet prepared in accordance with ASTM D3182.

PRECAUTIONS:

- Joints can be made using either a lap or skive-butt construction. Skive-butt joint should be covered with a cap strip (4 "wide x 1/8" thick) of plain chlorobutyl 2007.
- Swab mating surfaces of cap strip and lining with toluene solvent or CB tack cement 0147HE2S for longer open tack time during cap strip application.
- **Preheat cap strip for at least 10 minutes on a 120°F/43°C heat table.** Thoroughly stitch edges of cap strip so edges are completely sealed.