

# 2056

## BLENDED CHLOROBUTYL OVERLAY

March 2015

**Polycorp 2056** is a black 55A durometer blended chlorobutyl rubber lining. Use as overlay for 1056. It provides excellent chemical resistance at elevated temperatures. Operating temperature range is from -4°F (-20°C) to 220°F (104°C).

### APPLICATION NOTES:

- **Skive** – use open skive construction
- **Repair** – Same or chemical cure 2040. Refer to section 11 of application manual.
- **Cured Durometer** – Shore A durometer of top surface: 55 ± 5.
- A heated table to warm the rubber to 110–120°F (43°C) is recommended
- **Spark Test** – Refer to section 13 of the Application Manual

### ADHESIVE NOTES:

See Section 6 of the Polycorp Rubber Lining Application Manual for specific cementing / adhesion notes.

For proper adhesion, temperatures must be over 60°F (15°C) and must not exceed 120°F (49°C).

Use adhesives in well-ventilated area and always consult the material safety data sheet for specific precautions.

### CURING:

Cure time adjustments may be required to compensate for specific conditions. See Section 10 of the Application Manual for detailed instructions.

**Autoclave Method – Up to 1/4” thickness:** Slow rise to 250°F/121°C (15 psi). Hold 3 hours @ 250°F/121°C (15 psi).

**Internal Steam Method – Up to 1/4” thickness:** Slow rise to 250°F/121°C (15 psi). Hold 6 hours @ 250°F/121°C (15 psi).

**Atmospheric Steam Method – Up to 1/4” thickness:** Minimum 24 hours @ 212°F/100°C.

Coat	Polycorp Adhesive	Approved Equivalent
1 <sup>st</sup> Coat on Metal	N/A	N/A
2 <sup>nd</sup> Coat on Metal	N/A	N/A
3 <sup>rd</sup> Coat on Metal	N/A	N/A
4 <sup>th</sup> Coat on lining	N/A	N/A

## STORAGE:

Store in a cool and dry area.

Shelf Life	
Stored below 50°F (10°C)	180 days
Stored between 51 and 70°F	60 days
Stored between 71 and 90°F	45 days
Do not store above 90°F (32°C)	

Depending on storage conditions it may be possible to use rubber linings beyond the recommended shelf life however additional testing must be completed. Please contact Polycorp for recommended test procedures. A sample of the rubber lining can also be sent back to Polycorp for verification.

Storage, handling and application methods must conform to the Polycorp Rubber Lining Application Manual.

## TYPICAL PROPERTIES:

Property	Value	ASTM Test Method
Hardness (Face)	55A ± 5	D2240
Tensile Strength (min, psi)	1000	D412
Elongation at Break (min, %)	400	D412
Specific Gravity	1.21	D297
Adhesion to Metal (min, lbs)	25	D429
Operating Temperature Range for Optimum service Life	- 4°F (-20°C) to 220°F (104°C)	N/A

All physical property values developed and measured using a press-cured sample sheet prepared in accordance with ASTM D3182.

## PRECAUTIONS:

- Swab mating surfaces with toluene solvent. A solution made up of 10-15% cement in toluene can also be used on the mating surfaces for longer tack time during application.