

6511

BROMOBUTYL CAP STRIP

March 2015

Polycorp 6511 is a 50A durometer bromobutyl rubber lining. It provides superior temperature resistance in phosphoric acids and caustic solutions up to 260°F. Operating temperature range is from - 4°F (-20°C) to 260°F (127°C).

APPLICATION NOTES:

- **Skive** – Open skive construction.
- **Repair** – Same. Refer to section 11 of application manual.
- **Cured Durometer** – Shore Durometer of top surface: 50A ± 5.
- A heated table to warm the rubber to 110–120°F (43°C) is recommended
- **Spark Test** – Refer to section 13 of the Application Manual

ADHESIVE NOTES:

See Section 6 of the Polycorp Rubber Lining Application Manual for specific cementing / adhesion notes. For proper adhesion, temperatures must be over 60°F (15°C) and must not exceed 120°F (49°C). Use adhesives in well-ventilated area and always consult the material safety data sheet for specific precautions.

CURING:

Cure time adjustments may be required to compensate for specific conditions. See Section 10 of the Application Manual for detailed instructions.

Autoclave Method – Up to 1/4” thickness:

2 hours @ 292°F/144°C (45 psi).

Internal Steam Method – Up to 1/4” thickness:

8 hours @ 260°F/127°C (20 psi).

Atmospheric Steam Method – Up to 1/4” thickness:

Minimum 30 hours @ 212°F/100°C

Coat	Polycorp Adhesive	Approved Equivalent
1 st Coat on Metal	N/A	N/A
2 nd Coat on Metal	N/A	N/A
3 rd Coat on Metal	N/A	N/A
4 th Coat on lining	N/A	N/A

STORAGE:

Store in a cool and dry area.

Shelf Life	
Stored below 50°F (10°C)	180 days
Stored between 51 and 70°F	60 days
Stored between 71 and 90°F	45 days
Do not store above 90°F (32°C)	

Depending on storage conditions it may be possible to use rubber linings beyond the recommended shelf life however additional testing must be completed. Please contact Polycorp for recommended test procedures. A sample of the rubber lining can also be sent back to Polycorp for verification.

Storage, handling and application methods must conform to the Polycorp Rubber Lining Application Manual.

TYPICAL PROPERTIES:

Property	Value	ASTM Test Method
Hardness (Face)	50 A ± 5	D2240
Tensile Strength (min, psi)	1100	D412
Elongation at Break (min, %)	500 %	D412
Specific Gravity	1.40	D297
Adhesion to Metal (min, lbs)	25	D429
Operating Temperature Range for Optimum Service Life	- 4°F (-20°C) to 260°F (127°C)	N/A

All physical property values developed and measured using a press-cured sample sheet prepared in accordance with ASTM D3182.

PRECAUTIONS:

- Use 2" wide cap strip over skive-butt joint.
- Swab mating surfaces of cap strip and lining with toluene solvent. A solution made up of 10-15% cement in toluene can also be used on the cap strip for longer tack time and increase tack during cap strip application.
- **Preheat cap strip for at least 10 minutes on a 120°F/43°C heat table.** Thoroughly stitch edges of cap strip so edges are completely sealed.