

6585

March 2015

Polycorp 6585 is a black 65A durometer SBR lining with excellent abrasion resistance along with ozone and weather protection. For molding and pressure cure only!

APPLICATION NOTES:

- **Skive** – use open skive construction
- **Repair** – Same.
- **Cured Durometer** – Shore A Durometer of top surface: 65 ± 5.
- **Spark Test** – Refer to Section 13 of the application Manual

ADHESIVE NOTES:

See Section 6 of the Polycorp Rubber Lining Application Manual for specific cementing / adhesion notes. For proper adhesion, temperatures must be over 60°F (15°C) and must not exceed 120°F (49°C). Use adhesives in well-ventilated area and always consult the material safety data sheet for specific precautions.

CURING:

Cure time adjustments may be required to compensate for specific conditions. See Section 10 of the Application Manual for detailed instructions.

Autoclave Method – Up to 1/4” thickness:

Fast rise to 290°F/143°C (42 psi) cure for 45 minutes

Autoclave Method - > 1/4”to 1/2” thickness:

Fast rise to 290°F/143°C (42 psi) cure for 1 ½ hours

Coat	Polycorp Adhesive	Approved Equivalent
1 st Coat on Metal	C-90 Primer	Chemlok 289
2 nd Coat on Metal	C-91 Intermediate	Chemlok 290
3 rd Coat on Metal	C-202S Tack	Chemlok 286
4 th Coat on metal or lining	C-202S Tack	Chemlok 286

STORAGE:

Store in a cool and dry area.

Shelf Life	
Stored below 50°F (10°C)	180 days
Stored between 51 and 70°F	60 days
Stored between 71 and 90°F	45 days
Do not store above 90°F (32°C)	

Depending on storage conditions it may be possible to use rubber linings beyond the recommended shelf life however additional testing must be completed. Please contact Polycorp for recommended test procedures. A sample of the rubber lining can also be sent back to Polycorp for verification.

Storage, handling and application methods must conform to the Polycorp Rubber Lining Application Manual.

TYPICAL PROPERTIES:

Property	Value	ASTM Test Method
Hardness (Face)	65 A ± 5	D2240
Tensile Strength (min, psi)	2000	D412
Elongation at Break (min, %)	450	D412
Specific Gravity	1.17	D297
Adhesion to Metal (min, lbs)	25	D429
Operating Temperature Range for Optimum Service Life	- 40°F (-40°C) to 175°F (80°C)	N/A

All physical property values developed and measured using a press-cured sample sheet prepared in accordance with ASTM D3182.