

POLYCORP C-700 Chemical Cure Activator

May 2016

Polycorp C-700 Chemical cure activator for all rubber linings. Suitable for use with autoclave, open steam and chemical cures. Not for FDA application

TYPICAL PROPERTIES:

	C-700
Composition	A mixture of rubber chemicals dissolved in an organic solvent.
Color	Yellowish liquid
% NV by weight	33.1 %
Weight /gal.	7.80 +/- 0.30 lbs
Theoretical Coverage	300 sq. ft/ gal
Shelf Life	18 months from date of manufacture, unopened container 70°F- 80°F (21°C - 27°C) storage temperature

Application:

Polycorp C-700 cement can be applied by brush or roller. Once the rubber lining is installed, coat the surface of lining with 3 coats of C-700 allowing 30-45 minutes drying time between each coats. After the last coat has been applied wait for 24 hours to allow chemical to penetrate the lining before applying any heat source.

Safety:

Before using this product please refer to the Safety Data Sheet (SDS) for safe use and handling.