

# POLYCORP C-700

## Chemical Cure Activator

May 2014

**Polycorp C-700** Chemical cure activator for all rubber linings. Suitable for use with autoclave, open steam and chemical cures. Not for FDA application

**TYPICAL PROPERTIES:**

	<b>C-700</b>
Composition	A mixture of rubber chemicals dissolved in an organic solvent.
Color	Yellowish liquid
% NV by weight	33.1 %
Weight /gal.	7.80 +/- 0.30 lbs
Theoretical Coverage	300 sq. ft/ gal
Shelf Life	12 months from date of shipment, unopened container 70°F- 80°F (21°C - 27°C) storage temperature

**Application:**

Polycorp C-700 cement can be applied by brush or roller. Once the rubber lining is installed, coat the surface of lining with 3 coats of C-700 allowing 2 hours drying time between each coats. After the last coat has been applied wait for 24 hours to allow chemical to penetrate the lining before applying any heat source.

**Safety:**

Before using this product please refer to the Material Safety Data Sheet (MSDS) for safe use and handling.